



**WELDED STAINLESS STEEL ORNAMENTAL TUBING - ASTM A554**

WELDED STAINLESS STEEL ORNAMENTAL TUBING - ASTM A554							
<b>Chemistry</b>							
Grade:	Carbon (max.):	Manganese (max.):	Phosphorus (max.):	Sulphur (max.):	Silicon (max.):	Chromium:	Nickel:
304	0.080	2.000	0.045	0.030	1.000	18.00/20.00	8.00/11.00
304L	0.035	2.000	0.045	0.030	1.000	18.00/20.00	8.00/13.00
<b>Mechanical Properties (min.)</b>							
Grade:	Tensile Strength (psi):	Yield Strength (psi):	Elongation in 2":	RB:			
304	75,000	30,000	35	90			
304L	70,000	25,000	35	90			

The information listed is correct to the best of our knowledge. Wisconsin Steel & Tube Corporation assumes no responsibility for errors or omissions. Wisconsin Steel & Tube Corporation publishes this for guidance of their customers and reserves the right to add or delete items without notification.