



CARBON WELDED PIPE - ASTM A53

Chemistry				
Grade:	Carbon (max.):	Manganese (max.):	Phosphorus (max):	Sulphur (max.):
A53, Type F, Grade A	0.300	1.200	0.050	0.045
A53, Type E, Grade B	0.300	1.200	0.050	0.045
Mechanical Properties (min.)				
Grade:	Yield Strength (psi):	Tensile Strength (psi):		
A53, Type F, Grade A	30,000	48,000		
A53, Type E, Grade B	35,000	60,000		

The information listed is correct to the best of our knowledge. Wisconsin Steel & Tube Corporation assumes no responsibility for errors or omissions. Wisconsin Steel & Tube Corporation publishes this for guidance of their customers and reserves the right to add or delete items without notification.